



Flame-retardant bedding compound for XLPE insulation and HFFR sheathing.

■ Compound class

Bedding compound

■ Application examples: Insulation

2 XI 1 XLPE
2 YI 1 - 5 PE
9 YI 1 PP

■ Application examples: Sheathing

2 YM 3 HDPE
... PUR / TPU

■ Based on

EPR

acc. DIN / VDE 0207 part 22
acc. DIN / VDE 0207 part 2
acc. DIN / VDE 0207 part 7


acc. DIN / VDE 0207 part 3

■ Characteristics

Halogen-free flame retardant

■ Typical applications

Bedding compound for cables and wire with max. 90°C operating temperature at conductor.



Home



City



Industry

■ Features



For tandem process



Flame retardant



Halogen-free

PHYSICAL PROPERTIES

■ Physical properties

	Unit	Typical value	Test method
Density*	g/cm ³	1,81	DIN EN ISO 1183-1A
Hardness*	Shore A	85	DIN ISO 48-4
Mooney viscosity, ML (1+4) 100°C	MU	19	DIN ISO 289-1

ELECTRICAL PROPERTIES *

■ Major electrical properties

	Unit	Typical value	Test method
Volume resistivity (at 27°C)	Ω cm	≥ 10¹²	VDE 0472 Part 503
Surface resistivity (at 23°C)	Ω	≥ 10⁹	VDE 0472 Part 502


BURNING PROPERTIES *

■ Main burning properties	Unit	Typical value	Test method
LOI	%	35	ASTM D 2863 A
■ Acid gas emission	Unit	Typical value	Test method
pH (min.)	-	≥ 4,3	IEC 60754-2
Conductivity (max.)	μS cm-1	≤ 100	IEC 60754-2

* pressed plaques, 100°C / 5 min.

PROCESSING GUIDE

■ Extruder type	Standard extruders for elastomeric or thermoplastic processing
■ Screw configuration	Low compression screw with L/D of 12 to 25
■ Tooling	semi-compression or tube
■ Temperature profile extruder	The profile shown below may vary slightly depending on extruder type, head design & output.



■ Maximum mass temperature	90 – 100°C
■ Drying	Pre-drying of Melos FM Bedding Compounds is normally not necessary provided that the compound has been stored in the original sealed bags under cool (max. 30°C) and dry conditions.

STORAGE INFORMATION

■ Form & packaging	Pellets in sizes 5.5mm & 7.5mm PE-bags (25 kg), Octabins (1.000-2.000 kg), BigBags (max. 1.250 kg)
■ Shelf life	1 year after production

Note: The information given in this datasheet is believed to be accurate and reliable. However, no warranty, express or implied, or guarantee is given as to the suitability, accuracy, reliability or completeness of the information. This information does not hold us liable for damages or penalties resulting from following our suggestions or recommendations.